

DUPOXY COATING TC-100

High build, solvent free epoxy resin floor coating

Description

Dubond's Dupoxy Coating TC-100 is a solvent free system based on epoxy resins and curing agents specially selected for their ability to withstand chemical attack. The system consists of pre-weighed base & hardener components and a Dupoxy colour pack, all of which contain reactive elements that are essential to the installation of the system.

A slip resistant texture can be provided by the use of one of a range of Dubond Antislip Grains which have been carefully graded to ensure an even texture.

Uses

Dupoxy Coating TC-100 provides a hard wearing, chemical and abrasion resistant floor finish. It is ideally suited for use in wet areas where a high degree of resistance to chemicals, oils and grease is required such as ...

- Production assembly areas.
- Workshops / Warehouses.
- Dairies / Food Processing Unit
- Soft drinks production and bottling plants.
- Light Industrial Plants.
- Showrooms / Hospital / Hotels.

Advantages

- Durable, low maintenance costs.
- Proven against a wide range of industrial chemicals.
- Solvent free - no odour during application.
- Slip resistant - different textures available to suit conditions to avoid slipping.
- Liquid applied providing complete protection.
- Available in a wide range of colours to improve the working environment and identify slip hazard areas.

Specification

The epoxy resin floor coating shall be Dubond Coating TC-100 from Dubond. The total dry film thickness of the coating shall be a minimum of 400 microns and shall have a compressive strength of 70 N/mm², flexural strength of 40 N/mm² and a tensile strength of 20 N/mm². The floor shall be prepared and the coating mixed and applied in accordance with the manufacturer's current data sheet.

Design Criteria

Dupoxy coating TC-100 is applied as a floor Coating system comprising of two top coats (depending on the substrate conditions a primer might be required), each top coat to be a minimum of 200 microns thick. To provide a slip resistant texture, the first top coat can be dressed with Dubond Antislip Grains.

Properties

The following values were obtained when tested at 20°C and 30°C.

Properties	@ 20°C	@ 30°C
Pot life	40 min.	20 min.
Cure Time	24 hours	18 hours
Maximum time between coats	36 hours	15 hours
Light traffic use after	24 hours	18 hours
Full traffic use after resistance to chemical spillage compressive strength	48 hours 7 days	24 hours 5 days
Compressive strength	70 N / mm ²	
Flexural strength	40 N / mm ²	
Tensile strength	20 N / mm ²	
Water absorption (ASTM C 413 : 1996)	0.06%	
Shore D Hardness (ASTM D 2240 : 1996)	85	

Chemical Resistance

Fully cured Dupoxy Coating TC-100 samples have been tested in a wide range of aggressive chemicals commonly found in industrial environments. Tests were performed in accordance to ASTM D 543 standards over 168 hours (7 days) at 23°C ± 2.

ACIDS

Lactic acid 10%	Resistant
Citric acid 10%	Resistant
Acetic acid 10%	Resistant
Hydrochloric acid 50%	Resistant
Sulphuric acid 50%	Resistant
Nitric acid 25%	Resistant

ALKALIS

Sodium Hydroxide 50%	Resistant
Ammonia (0.880) 10%	Resistant

SOLVENTS

Petrol	Resistant
Oil	Resistant
Kerosene	Resistant
Butanol	Resistant
Skydrol	Resistant
Industrial Methylated Spirits	Resistant

OTHERS

Saturated Sugar Solution	Resistant
Urea (Saturated)	Resistant
Bleach 5%	Resistant

All the above properties have been determined by laboratory controlled tests and are in excess of those expected in practice. Never the less, success in use will be determined by the implementation of good housekeeping practices.

■ Instructions for use

Surface Preparation

The long term durability of any resin floor system is determined by the adhesive bond achieved between the flooring material and the substrate. It is most important therefore that substrates are correctly prepared prior to application.

New Concrete Floors

These should normally have been placed for at least 28 days and have a moisture content of less than 5%. Floors should be sound and free from contamination such as oil and grease mortar and paint splashes or curing compound residues. Excessive laitance can be removed by the use of mechanical methods. Dust and other debris should then be removed by vacuum cleaning.

Old Concrete Floors

A sound, clean substrate is essential to achieve maximum adhesion. Oil and grease penetration should be removed by the use of a proprietary chemical degreaser or by hot compressed air treatment.

Any damaged areas or surface irregularities should be repaired using Dupoxy Putty or Dupoxy SC 206

Priming

Priming is not normally required provide the substrate is sound, untreated and good quality nonporous concrete. If any doubts exist of the quality of the concrete.

Dupoxy Prime SFD should be mixed in the proportions supplied. Add the entire contents of the hardener can to the base can. When thoroughly mixed, preferably using slow speed drill and paddle, the primer should be applied in a thin continuous film, using rollers or stiff brushes. Work the primer well into the surface of the concrete taking care to avoid ponding or over application.

The primer should be left to achieve a tack-free condition before applying the top coat. A second coat of Primer may be required if the substrate is excessively porous.

Mixing the Coating

The base and hardner components of Dupoxy coating TC-100 should be thoroughly stirred before the tow and mixed together. The entire contents of the hardener container should be poured into the base container and the tow materials mixed thoroughly, then add the colour pot and mix for at least 3 minutes. The use of a heavy duty slow speed, flameproof or air driven drill fitted with a Mixing Paddle is desirable. Mix these components in the quantities supplied taking care to ensure all containers are scraped clean. Do not add solvent thinners at any time.

Standard Application

The first coat of Dupoxy coating TC-100 should be applied using a good quality medium haired pile roller, suitable for epoxy application, or squeegee to achieve a continuous coating. Ensure that loose hairs on the roller are removed before use. A minimum film thickness of 200 microns should be applied. This can be increased where specifications demand. When the base coat has reached initial cure (12 hours @ 20°C or 5 hours at 35°C). The top coat be applied by medium haired roller. at minimum film thickness of 200 microns. Care should be taken to ensure that a continuous film is achieved.

Antislip Application

If a slip resistant texture is required, the base coat shall be applied as per the base coat shall be applied as per the standard application, but at a minimum film thickness of 250 microns. The base coat should then be dressed with the chosen Dubond Antislip Grain. This should be done as soon as possible after laying. The recommended procedure is to completely blind the base coat i.e Apply excess dressing aggregate to completely obliterate the base coating.

Alternatively, the Dubond Antislip Grains can be broadcast a light random dressing to provide a less dense finish.

When the base coat has reached initial cure (12 hour @ 20°C or 5 hours at 35 °C), the excess aggregate should be vacuum cleaned from the surface.

The top coat can now be applied by medium haired roller, at a rate of 4.0m² / liter. Care should be taken to ensure that a continuous film is achieved and the rough surface, caused by the aggregate, is completely sealed. This top coat must be applied within 36 hours @ 20°C (15 hours @ 35°C) of the application of the first coat.

Expansion Joints

Expansion joints in the existing substrate must be retained and continued through the Dupoxy coating TC - 100 topping. Dubond has a range of joint sealants specifically designed for flooring, contact local Dubond office for advice.

Cleaning

Tools and equipments should be cleaned with Dupoxy Thinner immediately after use. Spillages should be absorbed with sand or sawdust and disposed of in accordance with local regulations.

Limitations

- Dupoxy coating TC-100 should not be applied on to surfaces known to, or likely to suffer from, rising dampness, potential osmosis problems or have a relative humidity greater than 75% as measured in accordance or have with BS 8203 Appendix A, or protimeter thermo hygrometer
- Dubond does not recommend acid etching method of floor preparation. If used, the method should be approved by the project consultant.
- In common with all epoxy materials, some sight shade changes may be experienced over the long term when placed in adverse exposure conditions. Any such change in shade is not regarded as being detrimental to performance.
- In case product is applied in areas of extreme temperature and high humidity, glossiness of product may be affected.

Technical Support

Dubond offers a comprehensive technical support service to specifiers, end users and contractors. It is also to offer onsite technical assistance an AutoCad facility and dedicated specification assistance in locations all over the India.

Estimating

Supply

Dupoxy Prime SFD	1 & 5 litre packs
Dupoxy Coating TC-100 (Including colour pack)	4.5 litre packs
Dubond Antislip Grains	20 kg bags
Dubond Thinner	5 & 20 litre cans

Standard Coverage

Dupoxy Prime SFD	6 - 8 m ² / litre
Dupoxy Coating TC-100 (Base Coat)	5.0 m ² / litre @ 200 microns WFT
Dubond coating TC-100 (Top Coat)	5.0 m ² / litre @ 200 microns WFT

Coverage - Antislip (approx) - For Medium Texture

Dupoxy Prime SFD	6 - 8 m ² / litre
Dupoxy Coating TC-100 (Base Coat)	4.0 m ² / litre @ 250 microns WFT
Antislip Grain No 2*	1.25 - 3.0 m ² / kg
Dupoxy Coating TC-100 (Top Coat)	4.0 m ² / litre @

Estimated system thickness - For Fine Texture

Dupoxy Prime SFD	6 - 8 m ² / litre
Dupoxy Coating TC-100 (Base Coat)	4.0 m ² / litre @ 250 microns WFT
Antislip Grain No 3*	1.25 - 3.0 m ² / kg
Dupoxy Coating TC-100 (Top Coat)	4.0 m ² / litre @
Estimated System Thickness	0.75 - 1.5 mm

* Depending on the type of texture required.

Note : Coverage figures given are theoretical - Due to wastage factors and the variety and nature of substrates practical.

Shelf Life

Dupoxy coating TC-100 has a shelf life of 12 months when stored in warehouse conditions below 35°C in the original, unopened packs.

Storage Conditions

Store under warehouse conditions, below 35°C in the original, unopened packs. For further information, refer to the Product Material Safety Data Sheet.

Cleaning and Disposal

Spillages of component products should be absorbed on to earth, sand or other inert material and transferred to a suitable vessel, Disposal of such spillages or empty packing should be in accordance with local waste disposal regulations.

Health & Safety

Dupoxy Coating TC-100, Dupoxy Prime SFD and Dupoxy Thinner should not come in contact with skin and eyes or be swallowed. Avoid prolonged inhalation of solvent vapours.

Some people are sensitive to epoxy resins, hardeners and solvents, goggles and a barrier cream should be used. Ensure adequate ventilation and if working in enclosed areas use suitable breathing apparatus.

If mixed resin comes into contact with the skin, it must be removed before it hardens with a resin removing cream followed by washing with soap.

Should accidental eye contamination occur, wash well with plenty of clean water and seek medical advice. If swallowed seek medical attention immediately. Do not induce vomiting.

Fire

Dupoxy Prime SFD and Dupoxy Thinner are flammable. Do not expose to naked flames or other source of ignition. No smoking during use. Containers should be tightly sealed when not in use. In the event of a fire, extinguish with CO₂ or foam.

Flash Points

Dupoxy Prime SFD	25°C
Dupoxy Thinner	33°C



Dubond Products (India) Pvt. Ltd.

C-3, 1001, Anushruti Tower, S.G. Highway, Thaltej,

Ahmedabad-380054. Gujarat - INDIA

Ph: 91-79-2685 6815 Fax: 91-79-2685 6816

Email: info@dubond.in Website: www.dubond.in

Customer Care : +91 9377177771

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.